

# Verification Report

Report No. SCL01I08087708

Page 1 of 35

## CENTRE TESTING INTERNATIONAL



**Applicant** Guangzhou Zhiyuan Electronics Stock Co.,LTD  
**Address** 2 Floor,NO.7 Building,Huangzhou Industrial Estate,Chebei Road,  
 Tianhe,Guangzhou,Guangdong China  
**Product Name** PCICAN Interface Board  
**Product Part No.** PCI-9820I  
**Client Reference** PCI-9810I、 PCI-9840I  
**Information**

**Conclusion**

Tested Sample	According to directive	Result
Submitted Sample	2011/65/EU	Pass

Pass means that the results shown on the report comply with the limits set by RoHS Directive 2011/65/EU.

Tested by Mike Qou

Reviewed by Meets Zheng

Approved by Danny Liu  
 Danny Liu  
 Technical Manager

Date Oct. 9, 2016



No.R177731658

Centre Testing International Group Co., Ltd.

Hongwei Industrial Zone, Bao'an 70 District, Shenzhen, Guangdong, China

# Verification Report

Report No. SCL01I08087708

Page 2 of 35

## Report Content

Sample Information.....	3
Test Requested.....	3
Photo(s) of the Product(s).....	3
Test Method.....	4
Test Result(s).....	5
Test Process.....	23
Photo(s) of the Tested Component(s).....	25
RoHS Directive Exemptions.....	29

# Verification Report

Report No. SCL01I08087708

Page 3 of 35


Sample Received Date Sep. 8, 2016  
Testing Period Sep. 8, 2016 to Oct. 9, 2016

## Test Requested

1. As specified by client, to screen Lead(Pb), Cadmium(Cd), Mercury(Hg), Chromium(Cr) and Bromine(Br) in the submitted sample(s) by XRF.
2. As specified by client, when screening results exceed the XRF screening limit in IEC 62321-3-1:2013 Ed.1.0, further use of chemical methods are required to test the Lead(Pb), Cadmium(Cd), Mercury(Hg), Hexavalent Chromium(Cr(VI)), Polybrominated Biphenyls(PBBs), Polybrominated Diphenyl Ethers(PBDEs) in the submitted samples.

## Photo(s) of the Product(s)

### PCICAN Interface Board



# Verification Report

Report No. SCL01I08087708

Page 4 of 35

## Test Method

### A. Screening limits for regulated elements according to IEC 62321-3-1:2013 Ed.1.0 (Unit: mg/kg)

Element	Polymers	Metals	Composite material
Pb	$BL \leq (700-3\sigma) < X$ $< (1300+3\sigma) \leq OL$	$BL \leq (700-3\sigma) < X$ $< (1300+3\sigma) \leq OL$	$BL \leq (500-3\sigma) < X < (1500+3\sigma)$ $\leq OL$
Cd	$BL \leq (70-3\sigma) < X < (130+3\sigma)$ $\leq OL$	$BL \leq (70-3\sigma) < X < (130+3\sigma)$ $\leq OL$	$LOD < X < (150+3\sigma) \leq OL$
Hg	$BL \leq (700-3\sigma) < X < (1300+3\sigma)$ $\leq OL$	$BL \leq (700-3\sigma) < X < (1300+3\sigma)$ $\leq OL$	$BL \leq (500-3\sigma) < X < (1500+3\sigma)$ $\leq OL$
Cr	$BL \leq (700-3\sigma) < X$	$BL \leq (700-3\sigma) < X$	$BL \leq (500-3\sigma) < X$
Br	$BL \leq (300-3\sigma) < X$	N/A	$BL \leq (250-3\sigma) < X$

### B. Chemical Test

Tested Item(s)	Test Method	Measured Equipment(s)	MDL	Limit
Lead (Pb)	IEC 62321-5:2013 Ed.1.0	ICP-OES	10 mg/kg	1000 mg/kg
	Refer to IEC 62321-5:2013 Ed.1.0	ICP-OES	10 mg/kg	
Cadmium (Cd)	IEC 62321-5:2013 Ed.1.0	ICP-OES	10 mg/kg	100 mg/kg
	Refer to IEC 62321-5:2013 Ed.1.0	ICP-OES	10 mg/kg	
Mercury (Hg)	IEC 62321-4:2013 Ed.1.0	ICP-OES	10 mg/kg	1000 mg/kg
	Refer to IEC 62321-4:2013 Ed.1.0	ICP-OES	10 mg/kg	
Hexavalent Chromium (Cr(VI))	IEC 62321:2008 Ed.1 Annex C	UV-Vis	10 mg/kg	1000 mg/kg
	IEC 62321-7-1:2015	UV-Vis	0.10 $\mu$ g/cm <sup>2</sup> (LOQ)	
Polybrominated Biphenyls (PBBs)	IEC 62321-6:2015	GC-MS	100 mg/kg	1000 mg/kg
Polybrominated Diphenyl Ethers (PBDEs)	IEC 62321-6:2015	GC-MS	100 mg/kg	1000 mg/kg

#### Remark:

- BL = Under the screening limit
- OL = Above the screening limit
- X = The range of needing to do further testing
- 3 $\sigma$  = The reproducibility of analytical instruments
- N/A = Not applicable
- LOD = Detection limit
- LOQ = Limit of Quantification, The LOQ of Hexavalent chromium is 0.10  $\mu$ g/cm<sup>2</sup>

# Verification Report

Report No. SCL01I08087708

Page 5 of 35

**Test Result(s)**

Sample No.	Sample Description	Tested Items	XRF Screening Test	Chemical Test (mg/kg)	Conclusion	Sample Received/ Resubmitted Date
1	PCB (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	IN	N.D.		
2	Silvery metal	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	N/A	/		
3	Silvery metal	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	N/A	/		
4	Silvery metal	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	IN	N.D.▼		
		Br(PBBs&PBDEs)	N/A	/		
5	Silvery metal	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	N/A	/		
6	Silvery metal	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	N/A	/		



# Verification Report

Report No. SCL01I08087708

Page 6 of 35

Sample No.	Sample Description	Tested Items	XRF Screening Test	Chemical Test (mg/kg)	Conclusion	Sample Received/ Resubmitted Date
7	Silvery metal	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	N/A	/		
8	Black plastic	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	IN	N.D.		
9	Silvery/light golden metal	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	N/A	/		
10	Silvery metal	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	N/A	/		
11	Black resistance (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
12	Black resistance (Tested as a whole)	Pb	IN	385	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	IN	N.D.		
		Br(PBBs&PBDEs)	BL	/		

# Verification Report

Report No. SCL01I08087708

Page 7 of 35

Sample No.	Sample Description	Tested Items	XRF Screening Test	Chemical Test (mg/kg)	Conclusion	Sample Received/ Resubmitted Date
13	Black resistance (Tested as a whole)	Pb	IN	N.D.	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	IN	N.D.		
		Br(PBBs&PBDEs)	BL	/		
14	Black resistance (Tested as a whole)	Pb	IN	66	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
15	Black resistance (Tested as a whole)	Pb	IN	676	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
16	Black resistance (Tested as a whole)	Pb	IN	1198 <sup>#1</sup>	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
17	Blue body (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
18	Silvery metal	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	N/A	/		

# Verification Report

Report No. SCL01I08087708

Page 8 of 35

Sample No.	Sample Description	Tested Items	XRF Screening Test	Chemical Test (mg/kg)	Conclusion	Sample Received/ Resubmitted Date
19	Black resistance (Tested as a whole)	Pb	OL	1477 <sup>#1</sup>	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	IN	N.D.		
		Br(PBBs&PBDEs)	BL	/		
20	Brown capacitance (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
21	Deep brown capacitance (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
22	Brown capacitance (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
23	Deep brown capacitance (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
24	Light brown capacitance (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		



# Verification Report

Report No. SCL01I08087708

Page 9 of 35

Sample No.	Sample Description	Tested Items	XRF Screening Test	Chemical Test (mg/kg)	Conclusion	Sample Received/ Resubmitted Date
25	Gray capacitance (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
26	Yellow capacitance (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
27	Beige-white plastic	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
28	Cupreous enamelled wire	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
29	Green enamelled wire	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
30	Black magnet	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	N/A	/		

# Verification Report

Report No. SCL01I08087708

Page 10 of 35

Sample No.	Sample Description	Tested Items	XRF Screening Test	Chemical Test (mg/kg)	Conclusion	Sample Received/ Resubmitted Date
31	Silvery metal	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	N/A	/		
32	Black inductance (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
33	Black inductance (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
34	Black inductance (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
35	Crystal oscillator (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	IN	N.D.		
		Cr(Cr(VI))	IN	N.D.		
		Br(PBBs&PBDEs)	BL	/		
36	Crystal oscillator (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		

# Verification Report

Report No. SCL01I08087708

Page 11 of 35

Sample No.	Sample Description	Tested Items	XRF Screening Test	Chemical Test (mg/kg)	Conclusion	Sample Received/ Resubmitted Date
37	Black audion (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
38	Black body (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
39	Silvery metal	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	N/A	/		
40	Black body (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
41	Silvery metal	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	N/A	/		
42	Black body (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		

# Verification Report

Report No. SCL01I08087708

Page 12 of 35

Sample No.	Sample Description	Tested Items	XRF Screening Test	Chemical Test (mg/kg)	Conclusion	Sample Received/ Resubmitted Date
43	Silvery metal	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	N/A	/		
44	Black body (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	IN	N.D.		
45	Silvery metal	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	N/A	/		
46	Black body (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
47	Silvery metal	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	N/A	/		
48	Black body (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	IN	N.D.		

# Verification Report

Report No. SCL01I08087708

Page 13 of 35

Sample No.	Sample Description	Tested Items	XRF Screening Test	Chemical Test (mg/kg)	Conclusion	Sample Received/ Resubmitted Date
49	Silvery metal	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	N/A	/		
50	Black body (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
51	Silvery metal	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	N/A	/		
52	Black resistance (Tested as a whole)	Pb	IN	46	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	IN	N.D.		
		Br(PBBs&PBDEs)	BL	/		
53	Black resistance (Tested as a whole)	Pb	OL	1402 <sup>#1</sup>	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
54	White capacitance (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		



# Verification Report

Report No. SCL01I08087708

Page 14 of 35

Sample No.	Sample Description	Tested Items	XRF Screening Test	Chemical Test (mg/kg)	Conclusion	Sample Received/ Resubmitted Date
55	Brown capacitance (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
56	Deep brown capacitance (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
57	Brown capacitance (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
58	Deep brown capacitance (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
59	Light brown capacitance (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
60	Yellow capacitance (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		

# Verification Report

Report No. SCL01I08087708

Page 15 of 35

Sample No.	Sample Description	Tested Items	XRF Screening Test	Chemical Test (mg/kg)	Conclusion	Sample Received/ Resubmitted Date
61	LED (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
62	Black audion (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
63	Black plastic	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	IN	N.D.		
64	Golden metal	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	N/A	/		
65	Black plastic	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	IN	Decabromodiphenyl ether:107; Others:N.D.		
66	Silvery metal	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	N/A	/		

# Verification Report

Report No. SCL01I08087708

Page 16 of 35

Sample No.	Sample Description	Tested Items	XRF Screening Test	Chemical Test (mg/kg)	Conclusion	Sample Received/ Resubmitted Date
67	White label with black printing	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
68	Black plastic with gray printing	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
69	PCB (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	IN	N.D.		
70	Silvery metal	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	N/A	/		
71	Black audion (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	IN	N.D.		
72	Black body (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	IN	N.D.		

# Verification Report

Report No. SCL01I08087708

Page 17 of 35

Sample No.	Sample Description	Tested Items	XRF Screening Test	Chemical Test (mg/kg)	Conclusion	Sample Received/ Resubmitted Date
73	Silvery metal	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	N/A	/		
74	Brown capacitance (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
75	Light brown capacitance (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
76	Black resistance (Tested as a whole)	Pb	IN	425	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
77	Cupreous enamelled wire	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
78	Red enamelled wire	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		

# Verification Report

Report No. SCL01I08087708

Page 18 of 35

Sample No.	Sample Description	Tested Items	XRF Screening Test	Chemical Test (mg/kg)	Conclusion	Sample Received/ Resubmitted Date
79	Green enamelled wire	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
80	Blue enamelled wire	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
81	Deep gray magnet	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	N/A	/		
82	Gray glue	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
83	Silvery metal	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	N/A	/		
84	Black body (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		



# Verification Report

Report No. SCL01I08087708

Page 19 of 35

Sample No.	Sample Description	Tested Items	XRF Screening Test	Chemical Test (mg/kg)	Conclusion	Sample Received/ Resubmitted Date
85	Silvery metal	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	N/A	/		
86	Black diode (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
87	Black body (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
88	Silvery metal	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	N/A	/		
89	Black body (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
90	Silvery metal	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	N/A	/		

# Verification Report

Report No. SCL01I08087708

Page 20 of 35

Sample No.	Sample Description	Tested Items	XRF Screening Test	Chemical Test (mg/kg)	Conclusion	Sample Received/ Resubmitted Date
91	Black body (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
92	Silvery metal	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	N/A	/		
93	Black audion (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
94	Green body (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
95	Silvery metal	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	N/A	/		
96	Red body (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		

# Verification Report

Report No. SCL01I08087708

Page 21 of 35

Sample No.	Sample Description	Tested Items	XRF Screening Test	Chemical Test (mg/kg)	Conclusion	Sample Received/ Resubmitted Date
97	Silvery metal	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	N/A	/		
98	Brown capacitance (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
99	IC (Tested as a whole)	Pb	OL	506	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
100	Red diode (Tested as a whole)	Pb	OL	177700 <sup>#1</sup>	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
101	Yellow capacitance (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		
102	White capacitance (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		

# Verification Report

Report No. SCL01I08087708

Page 22 of 35

Sample No.	Sample Description	Tested Items	XRF Screening Test	Chemical Test (mg/kg)	Conclusion	Sample Received/ Resubmitted Date
103	Crystal oscillator (Tested as a whole)	Pb	BL	/	PASS	Sep. 8, 2016
		Cd	BL	/		
		Hg	BL	/		
		Cr(Cr(VI))	BL	/		
		Br(PBBs&PBDEs)	BL	/		

### Remark:

- N.D. = Not Detected (<MDL or LOQ)
- MDL = Method Detection Limit
- mg/kg = ppm = parts per million
- /=Not tested
- IN= Uncertain, Further chemical test
- N/A= Not applicable
- BL = Under the screening limit
- OL = Further chemical test will be conducted while the result is above the screening limit.
- ▼The sample is negative for Cr(VI) – The Cr(VI) concentration is below 0.10 µg/cm<sup>2</sup>.  
The coating is considered a non-Cr(VI) based coating.
- When conducting the test for PBBs&PBDEs, XRF was introduced to screen Br Exclusively; When conducting the test for Hexavalent Chromium, XRF was introduced to screen Chromium exclusively.
- #1 According to the client's statement, the material of the sample(s) fall into exemption items 7(c)-I according to EU Directive 2011/65/EU: Electrical and electronic components containing lead in a glass or ceramic other than dielectric ceramic in capacitors, e.g. piezoelectronic devices, or in a glass or ceramic matrix compound.
- According to the client's statement, reference information see the following table:

Sample No.	Reference Report No.	Sample No. in Reference Report
68-70	SCL01I07315604	1-3
71-74	SCL01I07315604	8-11
75	SCL01I07315604	14
76	SCL01I07315604	16
77-83	SCL01I07315604	20-26
84-85	SCL01I07315604	29-30
86	SCL01I07315604	49

# Verification Report


Report No. SCL01I08087708

Page 23 of 35


## Test Process

### 1. Lead (Pb), Cadmium (Cd)

#### 1) IEC 62321-5:2013 Ed.1.0




#### 2) Refer to IEC 62321-5:2013 Ed.1.0



### 2. Mercury (Hg)

#### 1) IEC 62321-4:2013 Ed.1.0






# Verification Report

Report No. SCL01I08087708


Page 24 of 35

## 2) Refer to IEC 62321-4:2013 Ed.1.0




## 3. Hexavalent Chromium (Cr(VI))


### 1) Non-metal sample(s)



### 2) Plating/Metal sample(s)



## 4. Polybrominated Biphenyls(PBBs), Polybrominated Diphenyl Ethers(PBDEs)









# Verification Report

Report No. SCL01I08087708

Page 25 of 35

## Photo(s) of the tested component(s)











# Verification Report

Report No. SCL01I08087708

Page 26 of 35

## Photo(s) of the tested component(s)









# Verification Report

Report No. SCL01I08087708

Page 27 of 35

## Photo(s) of the tested component(s)










# Verification Report

Report No. SCL01I08087708

Page 28 of 35

## Photo(s) of the tested component(s)





# Verification Report

Report No. SCL01I08087708

Page 29 of 35

## Exempted Items of RoHS Directive

In accordance with Directive 2011/65/EU as amended, there are 41 exemption items in Annex III of 2011/65/EU altogether.

	Exemption	Scope and dates of applicability
1	Mercury in single capped (compact) fluorescent lamps not exceeding (per burner):	
1(a)	For general lighting purposes < 30 W: 5 mg	Expires on 31 December 2011; 3,5 mg may be used per burner after 31 December 2011 until 31 December 2012; 2,5 mg shall be used per burner after 31 December 2012.
1(b)	For general lighting purposes $\geq 30$ W and < 50 W: 5 mg	Expires on 31 December 2011; 3,5 mg may be used per burner after 31 December 2011.
1(c)	For general lighting purposes $\geq 50$ W and < 150 W: 5 mg	
1(d)	For general lighting purposes $\geq 150$ W: 15 mg	
1(e)	For general lighting purposes with circular or square structural shape and tube diameter $\leq 17$ mm	No limitation of use until 31 December 2011; 7 mg may be used per burner after 31 December 2011.
1(f)	For special purposes: 5 mg	
1(g)	For general lighting purposes < 30 W with a lifetime equal or above 20 000 h: 3,5 mg	Expires on 31 December 2017.
2(a)	Mercury in double-capped linear fluorescent lamps for general lighting purposes not exceeding (per lamp):	
2(a)(1)	Tri-band phosphor with normal lifetime and a tube diameter < 9 mm (e.g. T2): 5 mg	Expires on 31 December 2011; 4 mg may be used per lamp after 31 December 2011.
2(a)(2)	Tri-band phosphor with normal lifetime and a tube diameter $\geq 9$ mm and $\leq 17$ mm (e.g. T5): 5 mg	Expires on 31 December 2011; 3 mg may be used per lamp after 31 December 2011.
2(a)(3)	Tri-band phosphor with normal lifetime and a tube diameter > 17 mm and $\leq 28$ mm (e.g. T8): 5 mg	Expires on 31 December 2011; 3,5 mg may be used per lamp after 31 December 2011.
2(a)(4)	Tri-band phosphor with normal lifetime and a tube diameter > 28 mm (e.g. T12): 5 mg	Expires on 31 December 2012; 3,5 mg may be used per lamp after 31 December 2012.
2(a)(5)	Tri-band phosphor with long lifetime ( $\geq 25$ 000 h): 8 mg	Expires on 31 December 2011; 5 mg may be used per lamp after 31 December 2011.
2(b)	Mercury in other fluorescent lamps not exceeding (per lamp):	
2(b)(1)	Linear halophosphate lamps with tube > 28 mm (e.g. T10 and T12): 10 mg	Expires on 13 April 2012.
2(b)(2)	Non-linear halophosphate lamps (all diameters): 15 mg	Expires on 13 April 2016.

# Verification Report

Report No. SCL01I08087708

Page 30 of 35

2(b)(3)	Non-linear tri-band phosphor lamps with tube diameter > 17 mm (e.g. T9)	No limitation of use until 31 December 2011; 15 mg may be used per lamp after 31 December 2011.
2(b)(4)	Lamps for other general lighting and special purposes (e.g. induction lamps).	No limitation of use until 31 December 2011; 15 mg may be used per lamp after 31 December 2011.
3	Mercury in cold cathode fluorescent lamps and external electrode fluorescent lamps (CCFL and EEFL) for special purposes not exceeding (per lamp):	
3(a)	Short length ( $\leq 500$ mm)	No limitation of use until 31 December 2011; 3,5 mg may be used per lamp after 31 December 2011.
3(b)	Medium length ( $> 500$ mm and $\leq 1\ 500$ mm)	No limitation of use until 31 December 2011; 5 mg may be used per lamp after 31 December 2011.
3(c)	Long length ( $> 1500$ mm)	No limitation of use until 31 December 2011; 13 mg may be used per lamp after 31 December 2011.
4(a)	Mercury in other low pressure discharge lamps (per lamp).	No limitation of use until 31 December 2011; 15 mg may be used per lamp after 31 December 2011.
4(b)	Mercury in High Pressure Sodium (vapour) lamps for general lighting purposes not exceeding (per burner) in lamps with improved colour rendering index $R_a > 60$ :	
4(b)-I	$P \leq 155$ W	No limitation of use until 31 December 2011; 30 mg may be used per burner after 31 December 2011.
4(b)-II	$155$ W < $P \leq 405$ W	No limitation of use until 31 December 2011; 40 mg may be used per burner after 31 December 2011.
4(b)-III	$P > 405$ W	No limitation of use until 31 December 2011; 40 mg may be used per burner after 31 December 2011.
4(c)	Mercury in other High Pressure Sodium (vapour) lamps for general lighting purposes not exceeding (per burner):	
4(c)-I	$P \leq 155$ W	No limitation of use until 31 December 2011; 25 mg may be used per burner after 31 December 2011.
4(c)-II	$155$ W < $P \leq 405$ W	No limitation of use until 31 December 2011; 30 mg may be used per burner after 31

# Verification Report

Report No. SCL01I08087708

Page 31 of 35

		December 2011.
4(c)-III	P > 405 W	No limitation of use until 31 December 2011; 40 mg may be used per burner after 31 December 2011.
4(d)	Mercury in High Pressure Mercury (vapour) lamps (HPMV).	Expires on 13 April 2015.
4(e)	Mercury in metal halide lamps (MH)	
4(f)	Mercury in other discharge lamps for special purposes not specifically mentioned in this Annex.	
4(g)	Mercury in hand crafted luminous discharge tubes used for signs, decorative or architectural and specialist lighting and light-artwork, where the mercury content shall be limited as follows: (a) 20 mg per electrode pair + 0,3 mg per tube length in cm ,but not more than 80 mg, for outdoor applications and indoor applications exposed to temperatures below 20°C; (b) 15 mg per electrode pair + 0,24 mg per tube length in cm, but not more than 80 mg, for all other indoor applications.	Expires on 31 December 2018.
5(a)	Lead in glass of cathode ray tubes.	
5(b)	Lead in glass of fluorescent tubes not exceeding 0,2 % by weight.	
6(a)	Lead as an alloying element in steel for machining purposes and in galvanized steel containing up to 0,35 % lead by weight.	
6(b)	Lead as an alloying element in aluminium containing up to 0,4 % lead by weight.	
6(c)	Copper alloy containing up to 4% lead by weight.	
7(a)	Lead in high melting temperature type solders (i.e. lead- based alloys containing 85 % by weight or more lead).	
7(b)	Lead in solders for servers, storage and storage array systems, network infrastructure equipment for switching, signalling, transmission, and network management for telecommunications.	
7(c)-I	Electrical and electronic components containing lead in a glass or ceramic other than	

# Verification Report

Report No. SCL01I08087708

Page 32 of 35

	dielectric ceramic in capacitors, e.g. piezoelectronic devices, or in a glass or ceramic matrix compound.	
7(c)-II	Lead in dielectric ceramic in capacitors for a rated voltage of 125 V AC or 250 V DC or higher.	
7(c)-III	Lead in dielectric ceramic in capacitors for a rated voltage of less than 125 V AC or 250 V DC.	Expires on 1 January 2013 and after that date may be used in spare parts for EEE placed on the market before 1 January 2013.
7(c)-IV	Lead in PZT based dielectric ceramic materials for capacitors being part of integrated circuits or discrete semiconductors.	
8(a)	Cadmium and its compounds in one shot pellet type thermal cut-offs.	Expires on 1 January 2012 and after that date may be used in spare parts for EEE placed on the market before 1 January 2012.
8(b)	Cadmium and its compounds in electrical contacts.	
9	Hexavalent chromium as an anticorrosion agent of the carbon steel cooling system in absorption refrigerators up to 0,75 % by weight in the cooling solution.	
9(b)	Lead in bearing shells and bushes for refrigerant-containing compressors for heating, ventilation, air conditioning and refrigeration (HVACR) applications.	
11(a)	Lead used in C-press compliant pin connector systems.	May be used in spare parts for EEE placed on the market before 24 September 2010.
11(b)	Lead used in other than C-press compliant pin connector systems.	Expires on 1 January 2013 and after that date may be used in spare parts for EEE placed on the market before 1 January 2013.
12	Lead as a coating material for the thermal conduction module C-ring.	May be used in spare parts for EEE placed on the market before 24 September 2010.
13(a)	Lead in white glasses used for optical applications.	
13(b)	Cadmium and lead in filter glasses and glasses used for reflectance standards.	
14	Lead in solders consisting of more than two elements for the connection between the pins and the package of microprocessors with a lead content of more than 80 % and less than 85 % by weight.	Expires on 1 January 2011 and after that date may be used in spare parts for EEE placed on the market before 1 January 2011.
15	Lead in solders to complete a viable electrical connection between semiconductor die and	



# Verification Report

Report No. SCL01I08087708

Page 33 of 35

	carrier within integrated circuit flip chip packages.	
16	Lead in linear incandescent lamps with silicate coated tubes.	Expires on 1 September 2013.
17	Lead halide as radiant agent in high intensity discharge (HID) lamps used for professional reprography applications.	
18(a)	Lead as activator in the fluorescent powder (1 % lead by weight or less) of discharge lamps when used as speciality lamps for diazoprinting reprography, lithography, insect traps, photochemical and curing processes containing phosphors such as SMS ((Sr,Ba) <sub>2</sub> MgSi <sub>2</sub> O <sub>7</sub> :Pb).	Expires on 1 January 2011.
18(b)	Lead as activator in the fluorescent powder (1 % lead by weight or less) of discharge lamps when used as sun tanning lamps containing phosphors such as BSP (BaSi <sub>2</sub> O <sub>5</sub> :Pb).	
19	Lead with PbBiSn-Hg and PbInSn-Hg in specific compositions as main amalgam and with PbSn-Hg as auxiliary amalgam in very compact energy saving lamps (ESL).	Expires on 1 June 2011.
20	Lead oxide in glass used for bonding front and rear substrates of flat fluorescent lamps used for Liquid Crystal Displays (LCDs).	Expires on 1 June 2011.
21	Lead and cadmium in printing inks for the application of enamels on glasses, such as borosilicate and soda lime glasses.	
23	Lead in finishes of fine pitch components other than connectors with a pitch of 0, 65 mm and less.	May be used in spare parts for EEE placed on the market before 24 September 2010.
24	Lead in solders for the soldering to machined through hole discoidal and planar array ceramic multilayer capacitors.	
25	Lead oxide in surface conduction electron emitter displays (SED) used in structural elements, notably in the seal frit and frit ring.	
26	Lead oxide in the glass envelope of black light blue lamps.	Expires on 1 June 2011.
27	Lead alloys as solder for transducers used in high-powered (designated to operate for several hours at acoustic power levels of 125	Expired on 24 September 2010.



# Verification Report

Report No. SCL01I08087708

Page 34 of 35

	dB SPL and above) loudspeakers.	
29	Lead bound in crystal glass as defined in Annex I (Categories 1, 2, 3 and 4) of Council Directive 69/493/EEC.	
30	Cadmium alloys as electrical/mechanical solder joints to electrical conductors located directly on the voice coil in transducers used in high-powered loudspeakers with sound pressure levels of 100 dB (A) and more.	
31	Lead in soldering materials in mercury free flat fluorescent lamps (which e.g. are used for liquid crystal displays, design or industrial lighting).	
32	Lead oxide in seal frit used for making window assemblies for Argon and Krypton laser tubes.	
33	Lead in solders for the soldering of thin copper wires of 100 µm diameter and less in power transformers.	
34	Lead in cermet-based trimmer potentiometer elements.	
36	Mercury used as a cathode sputtering inhibitor in DC plasma displays with a content up to 30 mg per display.	Expired on 1 July 2010.
37	Lead in the plating layer of high voltage diodes on the basis of a zinc borate glass body.	
38	Cadmium and cadmium oxide in thick film pastes used on aluminium bonded beryllium oxide.	
39	Cadmium in colour converting II-VI LEDs (< 10 µg Cd per mm <sup>2</sup> of light-emitting area) for use in solid state illumination or display systems.	Expires on 1 July 2014.
40	Cadmium in photoresistors for analogue optocouplers applied in professional audio equipment.	Expires on 31 December 2013.

# Verification Report

Report No. SCL01I08087708

Page 35 of 35

41	Lead in solders and termination finishes of electrical and electronic components and finishes of printed circuit boards used in ignition modules and other electrical and electronic engine control systems, which for technical reasons must be mounted directly on or in the crankcase or cylinder of hand-held combustion engines (classes SH:1, SH:2, SH:3 of Directive 97/68/EC of the European Parliament and of the Council.	Expires on 31 December 2018.
----	---	------------------------------

\*\*\* End of Report \*\*\*

The test report is effective only with both signature and specialized stamp. The result(s) shown in this report refer only to the sample(s) tested. Without written approval of CTI, this report can't be reproduced except in full.